



## **FILMTEC™** Membranes

FILMTEC NF270 Nanofiltration Elements for Commercial Systems

**Features** The FILMTEC™ NF270 membrane elements are ideal for removing a high percentage of TOC and THM precursors with medium to high salt passage and medium hardness passage. The FILMTEC NF270 membrane is an ideal choice for surface water and ground water where good organic removal is desired with partial softening.


## **Product Specifications**

Product	Part Number	Active Area ft <sup>2</sup> (m <sup>2</sup> )	Applied Pressure psig (bar)	Permeate Flow Rate gpd (m <sup>3</sup> /d)	Stabilized Salt Rejection (%)
NF270-2540	149986	28 (2.6)	70 (4.8)	850 (3.2)	>97.0
NF270-4040	149987	82 (7.6)	70 (4.8)	2,500 (9.5)	>97.0

1. Permeate flow and salt rejection based on the following test conditions: 2,000 ppm MgSO4, 77°F (25°C) and 15% recovery at the pressure specified above.

2. Permeate flows for individual NF270-2540 elements may vary by -20% / +30%. NF270-4040 individual elements may vary -15% / +50%.

3. Developmental products available for sale.





FilmTec sells coupler part number 89055 for use in multiple element housings. Each coupler includes two 2-210 EPR o-rings, FilmTec part number 89255

	Dimensions – Inches (mm)				
Product	Α	В	C	D	
NF270-2540	40.0 (1,016)	1.19 (30)	0.75 (19)	2.4 (61)	
NF270-4040	40.0 (1,016)	1.05 (27)	0.75 (19)	3.9 (99)	
1. Refer to FilmTec Design C	Guidelines for multiple-element systems	S.		1 inch = 25.4 mm	

1. Refer to FilmTec Design Guidelines for multiple-element systems.

2. NF270-2540 has a tape outer wrap. NF270-4040 has a fiberglass outer wrap.

Operating Limits	<ul> <li>Membrane Type</li> <li>Maximum Operating Temperature</li> <li>Maximum Operating Pressure</li> <li>Maximum Feed Flow Rate - 4040 elements         <ul> <li>2540 elements</li> </ul> </li> <li>Maximum Pressure Drop - tape wrapped             <ul> <li>fiberglassed</li> <li>pH Range, Continuous Operation<sup>a</sup></li> <li>pH Range, Short-Term Cleaning (30 min.)<sup>b</sup></li> <li>Maximum Feed Silt Density Index</li> <li>Free Chlorine Tolerance<sup>c</sup></li> </ul> </li> </ul>	Polyamide Thin-Film Composite 113°F (45°C) 600 psi (41 bar) 16 gpm (3.6 m³/hr) 6 gpm (1.4 m³/hr) 13 psig (0.9 bar) 15 psig (1.0 bar) 2 - 11 1 - 12 SDI 5 < 0.1 ppm
	Maximum temperature for continuous operation above pH 10 is 0	

Maximum temperature for continuous operation above pH 10 is 95°F (35°C).

- b Refer to Cleaning Guidelines in specification sheet 609-23010 for NF90. с
- Under certain conditions, the presence of free chlorine and other oxidizing agents will cause premature membrane failure. Since oxidation damage is not covered under warranty, FilmTec recommends removing residual free chlorine by pretreatment prior to membrane exposure. Please refer to technical bulletin 609-22010 for more information.

™® Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

Form No. 609-00519-1206

Important Information Proper start-up of reverse osmosis water treatment systems is essential to prepare the membranes for operating service and to prevent membrane damage due to overfeeding or hydraulic shock. Following the proper start-up sequence also helps ensure that system operating parameters conform to design specifications so that system water quality and productivity goals can be achieved.

Before initiating system start-up procedures, membrane pretreatment, loading of the membrane elements, instrument calibration and other system checks should be completed.

Please refer to the application information literature entitled "Start-Up Sequence" (Form No. 609-02077) for more information.

Avoid any abrupt pressure or cross-flow variations on the spiral elements during start-up, shutdown, cleaning or other sequences to prevent possible membrane damage. During start-up, a gradual change from a standstill to operating state is recommended as follows:

- Feed pressure should be increased gradually over a 30-60 second time frame.
- Cross-flow velocity at set operating point should be achieved gradually over 15-20 seconds.
- Permeate obtained from first hour of operation should be discarded.

General	
Information	

Operation

Guidelines

- Keep elements moist at all times after initial wetting.
- If operating limits and guidelines given in this bulletin are not strictly followed, the limited warranty will be null and void.
- To prevent biological growth during prolonged system shutdowns, it is recommended that membrane elements be immersed in a preservative solution.
- The customer is fully responsible for the effects of incompatible chemicals and lubricants on elements.
- Maximum pressure drop across an entire pressure vessel (housing) is 30 psi (2.1 bar).
- Avoid static permeate-side backpressure at all times.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



Page 2 of 2

™® Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

Notice: The use of this product in and of itself does not necessarily guarantee the removal of cysts and pathogens from water. Effective cyst and pathogen reduction is dependent on the complete system design and on the operation and maintenance of the system.